

测试报告

: SHIN1711067164ML CN 编号

: 2017-11-14 日期

页码 : 1 of 2

客户名称: 上海北铭高强度钢材有限公司

客户地址: 上海市宝山区友谊路 1518 弄 2 号楼 1203-1208 室

低合金角钢 样品名称

63*63*6 产品规格

货号或批号 炉批号 5210274BB

生产商 安阳钢铁股份有限公司

购买商 安阳钢铁股份有限公司

材质牌号 Q345E

以上信息及样品由客户提供及确认,SGS 不承担证实客户提供信息的准确性、适当性和(或)完整性的责任。

测试要求 冲击测试


2017-11-07 收样日期

2017-11-07 测试开始时间

2017-11-14 测试结束时间

请见下页(除另有特别说明外,此报告结果仅对测试样品负责) 测试结果

> 通标标准技术服务(上海)有限公司 授权签名



史素娟

授权签字人





测试报告

编号 : SHIN1711067164ML_CN

日期 : 2017-11-14

页码 : 2 of 2

冲击测试:

测试方法: GB/T 229-2007

测试项目		测试条件	结果 (J)				要求	/- <u>-</u>
			1	2	3	平均值	(J)	结论
-	冲击吸收 能量	试片: 夏比 V 型缺口 试片尺寸: 55mm×10mm×5mm 温度: -40℃	21	32	66	40	全尺寸 ≥34 1/2 尺寸 ≥17	符合

注: 测试结果符合 GB/T 1591-2008 中牌号 Q345E 的要求。



在中华人民共和国境内,报告加盖 CMA 章,表示测试项目在资质认定范围内;未加盖 CMA 章,表示 部分/全部项目未在 CMA 资质认定范围内,结果仅供内部参考。



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic focuments at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-en-Condit

No.69, Block 1159, East Kang Qiao Road, Pudong District, Shanghai, China 201319 中国 • 上海 • 浦东康桥东路1159弄69号

t (86-21) 61196300 f (86-21) 68183122/68183920 www.sgsgroup.com.cn t (86-21) 61196300

f(86-21) 68183122/68183920 e sgs.china@sgs.com